



SMZ, a.s. Jelšava



B - BRIQUETTED

Description and physical properties :

Sintered magnesia produced by briquetting of fine ground caustic magnesia, subsequently fired.

Typical chemical parameters:	
MgO (%)	88,8 %
CaO (%)	2,8 %
Fe₂O₃ (%)	7,5%
SiO₂ (%)	0,5 %
Granulation (mm)	0 - 30
Bulk density (g/cm³)	3,30

Application	Temperature limit of application - 1750 °C. Suitable for basic refractories shaped and unshaped products and for the MgO-Cr ₂ O ₃ products.
Packing	Bulk in railway wagons; Big - Bags.

DBM FOR REFRACTORY PRODUCTION