



SMZ, a.s. Jelšava



TS -KG

Description and physical properties :

Sintered magnesia produced from natural magnesite by dressing and firing.

Typical chemical parameters:	
MgO (%)	88, 5 %
CaO (%)	2, 8 %
Fe₂O₃ (%)	5,2 %
SiO₂ (%)	2,5 %
Bulk density (g/cm³)	3 , 30

Application	Temperature limit of application - 1750 °C. Suitable for basic refractories shaped and unshaped products and for the MgO-Cr ₂ O ₃ products.
Packing	Bulk in railway wagons; Big - Bags.

DBM FOR REFRACTORY PRODUCTION